

ECO-BOND

HD 150

Structural Adhesive and Sealant

PERFORMANCE SPECIFICATIONS:

| | |
|--------------------------------------|------------|
| Shear Strength | 400 psi |
| Tensile Strength | 300 psi |
| Elongation | 400% |
| Peel Strength pli 90 degree | 34 pli |
| Application Temperature (Frost free) | 30 |
| Service Temperature | -40 to 200 |
| Slump/sag | 0 |
| Shore A Hardness | 45 |
| Solids | 100% |
| UV rating | Excellent |
| Glossy Finish | Yes |

GENERAL SPECIFICATIONS:

| | |
|---------------------------------|--------|
| Paintable | Yes |
| Permanently Elastic | Yes |
| Odor | Low |
| Moisture Curing | Yes |
| Staining | 0 |
| Shrinkage | Non |
| Non Flammable | Yes |
| Can be used in a confined space | Yes |
| Tack Free | 20 Min |
| Color | White |

GENERAL APPLICATIONS:

| | |
|---------------------------------------|--|
| Can be applied to: | |
| Wood | |
| Fiberglass | |
| Metal | |
| Drywall, Paneling | |
| Glass | |
| Siding, Wood, Cement, Vinyl, Aluminum | |
| PVC | |
| Laminate | |
| Concrete | |
| Tile | |
| Foam | |
| 2 non porous surfaces | |

GREEN ATTRIBUTES:

| | |
|--|------------|
| Materials listed on Prop 65 CA | None |
| Meets all California Standards | Yes |
| CARB Compliant | Yes |
| SARA compliant | Yes |
| LEED Compliant | Yes |
| SCAQMP Rule 1168 VOC | Yes |
| BAAQMD | Yes |
| Non Toxic | Yes |
| VOC rating at 249 degrees | 19 g/liter |
| Isocyanate Free | Yes |
| Urethane free | Yes |
| Solvent free | Yes |
| Not considered hazardous waste RCRA Criteria | Yes |
| Ethylene Glycol | None |
| Carcinogens Listed | None |
| Chemicals on the toxic chemical List | None |
| LEED Leadership In Energy and Environmental Design | Yes |
| NAHB Green Building Guidelines | Yes |



ECO-BOND

Setting a New Standard

N27 W23960 Paul RD Suite 202
Pewaukee WI 53072

1-800-326-8102

www.ecobondadhesives.com

doug@ecobondadhesives.com

ECO-BOND HD 150

Product Description

ECO-BOND HD 150 is a moisture curing, modified polymer adhesive/sealant designed for application in damp, dry or cold climates. ECO-BOND HD 150 is petroleum free, solvent free and contains no isocyanates. ECO-BOND HD 150 will not shrink upon curing, will not discolor when exposed to UV light, and can not "outgas" or bubble on damp surfaces urethane sealants often do. ECO-BOND HD 150 has excellent adhesion to most construction materials and resilient "elastomeric" properties. ECO-BOND HD 150 is capable of joint movement in excess of 50% compression and extension. Because it cures in wet or dry climate conditions and at low temperatures (30° F), ECO-BOND HD 150 can be used effectively in almost all applications.

Applicable Performance Standards

- ASTM C-920, Type S, Grade NS, Class 25, Uses NT, T, M, G, A and O
- Federal Specification TT-S-00230-C Type II, Class A
- Corps of Engineers CRD-C-541, Type II, Class A
- Canadian Standards Board CAN 19, 13-M82
- Conforms to OTC Rule for Sealants and Caulks
- Meets requirements of California Regs: CARB and SCAQMD
- Conforms to California Proposition 65
- Conforms to USDA Requirements for Non-food Contact

Green Standards:

- LEED 2.2 for New Construction and Major Renovations: Low Emitting Materials (Section 4.1) 1 Point
- NAHB Model Green Home Building Guidelines: 5 Global Impact Points
- VOC Content at 249° F: less than 19 grams/liter (including water), ASTM D2369, EPA Method 24

Colors

White, Gray, Tan

Application Instructions

1. Remove all dirt, oil, loose paint, frost and other contamination from all working surfaces with alcohol. DO NOT USE petroleum solvents such as mineral spirits or xylene.
2. Maintain ECO-BOND at room temperature before applying to ensure easy gunning.
3. Test and evaluate to ensure adequate adhesion.
4. Apply with a quality caulk gun.
5. Cut the cartridge nozzle at a 45° angle and to the desired gauge/length.
6. Puncture inner seal and carefully gun the sealant with a smooth, continuous bead.
7. If tooling is needed, do so within fifteen minutes.
8. Install all joint applications per ASTM and SWRI recommendations and guidelines. Joints shall be designed with a depth to width ratio of 1:2 (joint depth one-half the width).
9. Apply in temperatures above 30 degrees
10. Remove any standing water
11. Clean up wet ECO-BOND with alcohol, cured product maybe removed with abrasion.
12. Do not consume
13. Properly dispose of any unused product.
14. Keep out of reach of children

*Test and evaluate to ensure adequate adhesion.