ECO-BOND

CLEAR SEALANT

PERFORMANCE SPECIFICATIONS:

Shear Strength	200 psi
Tensile Strength	200-250 psi
Elongation	400-500%
Peel Strength pli 90 degree	22 pli
Application Temperature (Frost free)	30
Service Temperature	-40 to 200
Slump/sag	0
Shore A Hardness	27-33
Solids	100%
UV rating	Very good
Glossy Finish	Yes

GENERAL SPECIFICATIONS:

Paintable	Yes
Permanently Elastic	Yes
Odor	Low
Moisture Curing	Yes
Staining	0
Shrinkage	Non
Non Flammable	Yes
Can be used in a confined space	Yes
Tack Free	25 Min
Color	Clear

GENERAL APPLICATIONS:

Can be applied to:	
Wood	
Fiberglass	
Metal	
Drywall, Paneling	
Glass	
Siding, Wood, Cement, Vinyl, Aluminum	
PVC	
Laminate	
Concrete	
Tile	
Foam	
2 non porous surfaces	

GREEN ATTRIBUTES:

Materials listed on Prop 65 CA	None
Meets all California Standards	Yes
CARB Compliant	Yes
SARA compliant	Yes
LEED Compliant	Yes
SCAQMP Rule 1168 VOC	Yes
BAAQMD	Yes
Non Toxic	Yes
VOC rating at 249 degrees	13 g/liter
Isocyanate Free	Yes
Urethane free	Yes
Solvent free	Yes
Not considered hazardous waste RCRA Criteria	Yes
Ethylene Glycol	None
Carcinogens Listed	None
Chemicals on the toxic chemical List	None
LEED Leadership In Energy and Environmental Design	Yes
NAHB Green Building Guidelines	Yes



ECO-BOND

Setting a New Standard

N27 W23960 Paul RD Suite 202 Pewaukee WI 53072

1-800-326-8102

www.ecobondadhesives.com

dan@ecobondadhesives.com

ECO-BOND CLR125

Product Description

ECO-BOND CLR 125 is a moisture curing, modified polymer adhesive/sealant designed for application in damp, dry or cold clin ECO-BOND CLR 125 is petroleum free, solvent free and contains no isocyanates. ECO-BOND CLR 125 will not shrink upon cu will not discolor when exposed to UV light, and can not "out-gas" or bubble on damp surfaces urethane sealants often do. ECO-BOND CLR 125 has excellent adhesion to most construction materials and resilient "elastomeric" properties. ECO-BOND CLR capable of joint movement in excess of 25% compression and extension. Because it cures in wet or dry climate conditions and temperatures (30° F), ECO-BOND CLR 125 can be used effectively in almost all applications.

Applicable Performance Standards

- ASTM C-920, Type S, Grade NS, Class 25, Uses NT, T, M, G, A and O
- Federal Specification TT-S-00230-C Type II, Class A
- Corps of Engineers CRD-C-541, Type II, Class A
- Canadian Standards Board CAN 19, 13-M82
- · Conforms to OTC Rule for Sealants and Caulks
- Meets requirements of California Regs: BAAQMD, CARB and SCAQMD
- Conforms to California Proposition 65
- Conforms to USDA Requirements for Non-food Contact

Green Standards:

- LEED 2.2 for New Construction and Major Renovations: Low Emitting Materials (Section 4.1) 1 Point
- NAHB Model Green Home Building Guidelines: 5 Global Impact Points
- VOC Content at 249° F: less than 13 grams/liter (including water), ASTM D2369, EPA Method 24

Colors

Clear

Application Instructions

1. Remove all dirt, oil, loose paint, frost and other contamination from all working surfaces with alcohol. DO NOT USE petroleun solvents such as mineral spirits or xylene.


2. Maintain ECO-BOND at room temperature before applying to ensure easy gunning.

- 3. Test and evaluate to ensure adequate adhesion.
- 4. Apply with a quality caulk gun.
- 5. Cut the cartridge nozzle at a 45° angle and to the desired gauge/length.
- 6. Puncture inner seal and carefully gun the sealant with a smooth, continuous bead.
- 7. If tooling is needed, do so within fifteen minutes.

8. Install all joint applications per ASTM and SWRI recommendations and guidelines. Joints shall be designed with a depth to v ratio of 1:2 (joint depth one-half the width).

- 9. Apply in temperatures above 30 degrees
- 10. Remove any standing water
- 11. Clean up wet ECO-BOND with alcohol, cured product maybe removed with abrasion.
- 12. Do not consume
- 13. Properly dispose of any unused product.
- 14. Keep out of reach of children

*Test and evaluate to ensure adequate adhesion.



nates. ıring, -125 is at low

n

width